rch Title: 01-857a.opt Use cpacrb - Brian Crouch, S260 : 92-054171, Page 1 of 1, Wed Apr 18 11:32:24, VIEWED MARKED

Compsn is made by adding a suitable amt. of water reducing agent, fly ash and amorphous silica fines in which the fly ash discharged on firing coal is up to 20 microns in size. Resulting fly ash is then kneaded with aggregate and water.

USE - Used for water-light concrete for use at the underground Full Patentees: Shikoku Sogo Kenkyu; Taisel Construction KK parts. (6pp Dwg.No.0/4) Cement compsn. for water-tight concrete - has amorphous silica lines contg. discharged fly ash of specified size which is then kneaded with aggregate and water SHIKOKU SOGO KENKYU (TAKJ) C04b-22/06 C04b-24 C04b-28/04 C92-024645 054171/07 102 SHIK-17.04.90 KOKU SOGO KENKYU (TAKJ)
17.04.90-JP-102233 (07.01.92) C04b-14/02 C04b-18/08 C04b-20 L(2-D13, 2-D14Q)

P